

(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 1 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

(The following sample(s) was/were submitted and identified by the applicant

as)

IRM
EVERLIGHT
NO.6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN
TEL:886-2685-6688
FAX:886-2685-6699
E-MAIL: lindawang@everlight.com
LI LING WANG
IRM-2xxx/3xxx/5xxx/6xxx/7xxx/8xxx SERIES
Sampling Product: IRM-3638J7F114-SGS-15-Mar-2024
Receiver
0.4497 g
IRM-2xxx/3xxx/5xxx/6xxx/7xxx/8xxx SERIES
Sampling Product: IRM-3638J7F114
Y240127I0502AAK
China
CUTTING
RoHS: IEC 62321, Halogen: BS EN 14582
Cd, Pb, Hg: 2 mg/kg, PBBs/PBDEs: 5 mg/kg, Halogen: 50 mg/kg

(Sample Submitted By) : (EVERLIGHT ELECTRONICS CO., LTD.)

(Sample Receiving Date) : 06-Mar-2024

(Testing Period) : 06-Mar-2024 to 15-Mar-2024

(Test Results) : (Please refer to following pages).





PIN CODE: 8E32B7F



(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 2 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

(Test Requested) : (1) RoHS 2011/65/EU Annex II (EU) 2015/863

, DBP, BBP, DEHP, DIBP (As specified

by client, with reference to RoHS 2011/65/EU Annex II and amending Directive (EU) 2015/863 to determine Cadmium, Lead, Mercury, Cr(VI), PBBs, PBDEs, DBP,

BBP, DEHP, DIBP contents in the submitted sample(s).)

(2) PAHs (As specified by client, to test PAHs and

other item(s).)

(Conclusion) : (1) , DBP, BBP,

DEHP, DIBP RoHS 2011/65/EU Annex II (EU) 2015/863

(Based on the performed tests on submitted sample(s), the test results of Cadmium, Lead, Mercury, Cr(VI), PBBs, PBDEs, DBP, BBP, DEHP, DIBP comply with the limits as set by RoHS Directive (EU) 2015/863 amending Annex II

to Directive 2011/65/EU.)

(2) (A fPS) GS

PAHs 3 (Based upon the performed tests on the submitted sample(s), the test results of PAHs (15 items) comply with the limits of PAHs requirement (Category 3) Other consumer products as set by German

Committee on Product Safety (AfPS) GS PAHs.)

(Test Part Description)

No.1 : (BODY)

No.2 : (PLATING LAYER OF SILVER COLORED METAL PIN)
No.3 : (BASE MATERIAL OF SILVER COLORED METAL PIN)

No.4 : () (SILVER COLORED METAL PIN (INCLUDING THE PLATING LAYER))

(Test Results)

(Test Items)	(Method)	(Unit)	MDL		(Result)		(Limit)
((**************************************	(=:)		No.1	No.2	No.3	, ,
(Cd) (Cadmium (Cd))	IEC 62321-5: 2013	mg/kg	2	n.d.			100
	(AA); the mafagraph of the IEC (2221						
(Pb) (Lead (Pb))	(With reference to IEC 62321-5: 2013, analysis was	mg/kg	2	n.d.			1000
	performed by ICP-OES.)						



(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 3 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

(Test Items)	(Method)	(Unit)	MDL		(Result)		(Limit)
,				No.1	No.2	No.3	1
(Hg) (Mercury (Hg))	IEC 62321-4: 2013+ AMD1: 2017 (With reference to IEC 62321-4: 2013+ AMD1: 2017, analysis was performed by ICP-OES.)	mg/kg	2	n.d.			1000
Cr(VI) (Hexavalent Chromium Cr(VI))	IEC 62321-7-2: 2017 - (With reference to IEC 62321-7-2: 2017, analysis was performed by UV-VIS.)	mg/kg	80	n.d.			1000
(Monobromobiphenyl)		mg/kg	5	n.d.			-
(Dibromobiphenyl)		mg/kg	5	n.d.			-
(Tribromobiphenyl)		mg/kg	5	n.d.			-
(Tetrabromobiphenyl)	Ţ	mg/kg	5	n.d.			-
(Pentabromobiphenyl)		mg/kg	5	n.d.			-
(Hexabromobiphenyl)		mg/kg	5	n.d.			-
(Heptabromobiphenyl)		mg/kg	5	n.d.			-
(O ctabrom obiphenyl)		mg/kg	5	n.d.			-
(Nonabromobiphenyl)	IEC 62321-6: 2015	mg/kg	5	n.d.			-
(Decabromobiphenyl)	/ (With	mg/kg	5	n.d.			-
(Sum of PBBs)	reference to IEC 62321-6:	mg/kg	-	n.d.			1000
(Monobromodiphenyl ether)	2015, analysis was performed	mg/kg	5	n.d.			-
(Dibromodiphenyl ether)	by GC/MS.)	mg/kg	5	n.d.			-
(Tribromodiphenyl ether)	by Gorivia.)	mg/kg	5	n.d.			-
(Tetrabromodiphenyl ether)		mg/kg	5	n.d.			-
(Pentabromodiphenyl ether)		mg/kg	5	n.d.			-
(Hexabromodiphenyl ether)		mg/kg	5	n.d.			-
(Heptabromodiphenyl ether)	n	mg/kg	5	n.d.			-
(Octabromodiphenyl ether)		mg/kg	5	n.d.			-
(Nonabromodiphenyl ether)		mg/kg	5	n.d.			-
(Decabromodiphenyl ether)		mg/kg	5	n.d.			-
(Sum of PBDEs)		mg/kg	-	n.d.			1000



(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 4 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

(Test Items)	(Method)	(Unit)	MDL		(Result)		(Limit)
	(,	(=:,		No.1	No.2	No.3	, ,
(BBP) (Butyl benzyl phthalate (BBP))		mg/kg	50	n.d.			1000
(DBP) (Dibutyl phthalate (DBP))		mg/kg	50	n.d.			1000
(2-) (DEHP) (Di- (2-ethylhexyl) phthalate (DEHP))		mg/kg	50	n.d.			1000
(DIBP) (Diisobutyl phthalate (DIBP))	IEC 62321-8: 2017 / (With reference to IEC 62321-8:	mg/kg	50	n.d.			1000
(DIDP) (Diisodecyl phthalate (DIDP)) (CAS No.: 26761-40-0, 68515-49-1)		mg/kg	50	n.d.			-
(DINP) (Diisononyl phthalate (DINP)) (CAS No.: 28553-12-0, 68515-48-0)		mg/kg	50	n.d.			-
(DNOP) (Di-n- octyl phthalate (DNOP)) (CAS No.: 117-84-0)		mg/kg	50	n.d.			-
(DNPP) (Di-n- pentyl phthalate (DNPP)) (CAS No.: 131-18-0)	2017, analysis was performed by GC/MS.)	mg/kg	50	n.d.			-
(DNHP) (Di-n-hexyl phthalate (DNHP)) (CAS No.: 84-75-3)		mg/kg	50	n.d.			-
(2-) (DMEP) (Bis(2-methoxyethyl) phthalate (DMEP)) (CAS No.: 117-82-8)		mg/kg	50	n.d.			-
(DMP) (Dimethyl phthalate (DMP)) (CAS No.: 131-11-3)		mg/kg	50	n.d.			-
(DIOP) (Diisooctyl phthalate (DIOP)) (CAS No.: 27554-26-3)		mg/kg	50	n.d.			-



(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 5 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

			MDL		<i>(</i> =)		
(Test Items)	(Method)	(Unit)		(Result)			(Limit)
(DNNP) (Di-n-	IEC 62321-8: 2017	ma/ka	50	No.1 n.d.	No.2	No.3	
nonyl phthalate (DNNP)) (CAS No.:	/ (With	mg/kg	30	H.G.			-
84-76-4)	reference to IEC 62321-8:						
	2017, analysis was performed						
	by GC/MS.)						
	IEC 62321: 2008	mg/kg	5	n.d.			-
(HBCDD) (- HBCDD, - HBCDD, -	/ (With						
HBCDD) (Hexabromocyclododecane	reference to IEC 62321: 2008,						
(HBCDD) and all major diastereoisomers identified (-	analysis was performed by						
HBCDD, - HBCDD, - HBCDD)) (CAS	GC/MS.)						
No.: 25637-99-4, 3194-55-6 (134237-							
51-7, 134237-50-6, 134237-52-8))							
(F) (Fluorine (F)) (CAS No.: 14762-		mg/kg	50	n.d.			-
94-8)							
(CI) (Chlorine (CI)) (CASNo.:	BS EN 14582: 2016	mg/kg	50	325			-
22537-15-1)	(With reference						
(Br) (Bromine (Br)) (CAS No.:	to BS EN 14582: 2016, analysis	mg/kg	50	n.d.			-
10097-32-2)	was performed by IC.)	//	F.0				
(I) (lodine (I)) (CAS No.: 14362-44-8)		mg/kg	50	n.d.			-
(PFOS and its	CEN/TS 15968: 2010	mg/kg	0.01	n.d.			_
salts) (CAS No.: 1763-23-1 and its	3217,13 13,330. 2313	1119/119	0.01	man			
salts)	(With reference to CEN/TS						
	15968: 2010, analysis was						
	performed by LC/MS/MS.)						
(PFOA and its salts)	CEN/TS 15968: 2010	mg/kg	0.01	n.d.			-
(CAS No.: 335-67-1 and its salts)							
	(With reference to CEN/TS						
	15968: 2010, analysis was						
	performed by LC/MS/MS.)						



(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 6 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

(Test Items)	(Method)	(Unit)	MDL		(Result)		(Limit)
				No.1	No.2	No.3	Ī
(Polycyclic Aromatic Hydrocarbons) (PAHs)							
(a) (Benzo[a]pyrene) (CAS No.: 50-32-8)		mg/kg	0.2	n.d.			
(e) (Benzo[e]pyrene) (CAS No.: 192-97-2)		mg/kg	0.2	n.d.			
(Benzo[a]anthracene) (CAS No.: 56-55-3)		mg/kg	0.2	n.d.			
(b) (Benzo[b]fluoranthene) (CAS No.: 205-99-2)		mg/kg	0.2	n.d.			
(j) (Benzo[j]fluoranthene) (CAS No.: 205-82-3)		mg/kg	0.2	n.d.			
(k) (Benzo[k]fluoranthene) (CAS No.: 207-08-9)		mg/kg	0.2	n.d.			
(Chrysene) (CAS No.: 218-01-9)	A fPS GS 2019:01 PAK	mg/kg	0.2	n.d.			
(Dibenzo[a,h]anthracene) (CAS No.: 53-70-3)	/ (With reference to AfPS GS 2019:01	mg/kg	0.2	n.d.			
(Benzo[g,h,i]perylene) (CAS No.: 191-24-2)	PAK, analysis was performed by GC/MS.)	mg/kg	0.2	n.d.			
(Indeno[1,2,3-c,d]pyrene) (CAS No.: 193-39-5)		mg/kg	0.2	n.d.			
(Anthracene) (CAS No.: 120-12-7)		mg/kg	0.2	n.d.			
(Fluoranthene) (CAS No.: 206-44-0)		mg/kg	0.2	n.d.			
(Phenanthrene) (CAS No.: 85-01-8)	-	mg/kg	0.2	n.d.			
(Pyrene) (CAS No.: 129-00-0)		mg/kg	0.2	n.d.			
(Naphthalene) (CAS No.: 91-20-3)		mg/kg	0.2	n.d.			
15 (Sum of 15 PAHs)		mg/kg	-	n.d.			



(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 7 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

			MDL				
(Test Items)	(Method)	(Unit)			(Result)		(Limit)
				No.1	No.2	No.3	
(Be) (Beryllium (Be)) (CAS No.: 7440-41-7)	US EPA 3052: 1996 (With reference to US EPA 3052: 1996, analysis was performed by ICP- OES.)	mg/kg	2	n.d.			-
(Cd) (Cadmium (Cd))	IEC 62321-5: 2013 (IEC 62321-5: 2013 application of modified	mg/kg	2		n.d.		100
(Pb) (Lead (Pb))	digestion by surface etching, analysis was performed by ICP- OES.)	mg/kg	2		48.3		1000
(Hg) (Mercury (Hg))	IEC 62321-4: 2013+ AMD1: 2017 (IEC 62321-4: 2013+AMD1: 2017 application of modified digestion by surface etching, analysis was performed by ICP- OES.)	mg/kg	2		n.d.		1000
(Cd) (Cadmium (Cd))	IEC 62321-5: 2013 (With reference to IEC 62321-5: 2013,	mg/kg	2			n.d.	100
(Pb) (Lead (Pb))	analysis was performed by ICP-OES.)		2			n.d.	1000
(Hg) (Mercury (Hg))	IEC 62321-4: 2013+ AMD1: 2017 (With reference to IEC 62321-4: 2013+ AMD1: 2017, analysis was performed by ICP-OES.)	mg/kg	2			n.d.	1000



(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 8 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

	(Test Items)	(Method)	(Unit)	MDL		(Result)		(Limit)
					No.1	No.2	No.3	
(#2)		IEC 62321-7-1: 2015 - (With reference to IEC 62321-7- 1: 2015, analysis was performed by UV-VIS.)		0.1		n.d.	n.d.	-

(Test Items)	(Method)	(Unit)	MDL	(Result)	(Limit)
	US EPA 3050B: 1996 (With reference to US EPA 3050B: 1996, analysis was performed by ICP-OES.)	mg/kg	2	n.d.	-

•	Note)	
	mg/kg = ppm 0.1wt% = 0.1% = 1000ppm	
2.	MDL = Method Detection Limit ()	
3.	n.d. = Not Detected (); MDL / Less than MDL	
4.	"-" = Not Regulated ()	
5.	"" = Not Conducted ()	
6.	(#2) =	
	a. $0.13 \mu g/cm^2$.	/ The sample is positive for Cr(VI) if the Cr(VI)
	concentration is greater than 0.13 µg/cm ² . The sample coa	ating is considered to contain Cr(VI).
	b. n.d. ($0.10 \mu g/cm^2$)	. / The sample is negative for Cr(VI) if Cr(VI) is
	n.d. (concentration less than $0.10 \mu\text{g/cm}^2$). The coating is c	considered a non-Cr(VI) based coating
	c. $0.10 0.13 \mu \text{g/cm}^2$. / The result between 0.10 µg/cm² and
	$0.13\mu g/cm^{2}$ is considered to be inconclusive - unavoidabl	e coating variations may influence the determination.
7.	ILAC-G8:09/2019 (W=0)	
	(Unless otherwise stated, the	decision rule for conformity reporting is based on
	Binary Statement for Simple Acceptance Rule (w=0) stated	in ILAC-G8:09/2019. According to this rule, the
	judgement of conformity is based on the comparing test r	esults with limits.)



(No.): ETR24301210 (Date): 15-Mar-2024

(Page): 9 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

PAHs Remark

(AfPS): GSPAHs

AfPS (German commission for Product Safety): GS PAHs requirements

	1 (Category 1)	2 (Category 2)		3 (Cate	egory 3)
(Parameter)	(30) 2009/48/EC 3 (Materials intended to be placed in the mouth, or materials in toys (Directive 2009/48/EC) or articles for children up to 3	are not in Category 1, with intended or foreseeable long-term i		covered by Catego	30 erials not ry 1 or 2, with eable short-
	years of age with intended long-term skin contact (> 30 seconds))	a. 14 (Use by children under 14)	b. (Other consumer products)	a. 14 (Use by children under 14)	b. (Other consumer products)
Naphthalene	< 1	< 2)	< 10)
Phenanthrene					
Anthracene	< 1 Sum	< 5 Sum	< 10 Sum	< 20 Sum	< 50 Sum
Fluoranthene	< 1 Suili	< 5 Sui i i	< 10 Sui ii	< 20 Suiti	< 50 Suiti
Pyrene					
Benzo[a]anthracene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Chrysene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Benzo[b]fluoranthene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Benzo[j]fluoranthene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Benzo[k]fluoranthene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Benzo[a]pyrene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Benzo[e]pyrene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Indeno[1,2,3-c,d] pyrene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Dibenzo[a,h]anthracene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
Benzo[g,h,i]perylene	< 0.2	< 0.2	< 0.5	< 0.5	< 1
15 PAH (Sum of 15 PAH)	< 1	< 5	< 10	< 20	< 50

(Unit) mg/kg



(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 10 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
(NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

PFAS Remark					
PFAS	PFAS		PFAS		
			PFAS		PFAS
	(PFA S		PFAS)

(The quantitative technology of PFAS is to analyze the specific structure of PFAS substances. However, PFAS acid and its salts with the same carbon number group have the same specific structure that can be identified. The tested results of the analyzed specific structure cannot be distinguished to identify the contribution from PFAS acid or its salts. Therefore, the tested results display the sum of concentrations of PFAS acids and its salts with the same carbon number group. The concentration of PFAS substances in the below table have been included in the tested results, please refer to the table for relevant information: (The listed PFAS substances are examples only, it do not include all PFAS salts with the same carbon number group.))

		CAS No.
(Group Name)	(Substance Name)	
PFOS, & (PFOS, its salts & derivatives)	(Perfluorooctane sulfonates) (PFOS)	1763-23-1
	(PFO S-K) Potassium perfluorooctanesulfonate (PFOS-K)	2795-39-3
	(PFO S-Li) Perfluorooctanesulfonic acid, lithium salt (PFOS-Li)	29457-72-5
	$\label{eq:pfosnh4} \mbox{(PFOS-NH}_4)$ Perfluorooctanesulfonic acid, ammonium salt (PFOS-NH $_4$)	29081-56-9
	(PFOS-NH(OH) ₂) Perfluorooctane sulfonate diethanolamine salt (PFOS-NH(OH) ₂)	70225-14-8
	$(PFO S-N (C_2H_5)_4) \\ Perfluorooctanesulfonic \\ acid,tetraethylammonium salt (PFOS-N(C_2H_5)_4)$	56773-42-3
	(PFOS-DDA) N-decyl-N,N-dimethyldecan-1-aminium 1,1,2,2,3,3,4,4,5,5,6,6,7,7,8,8,8- heptadecafluorooctane-1-sulfonate (PFOS-DDA)	251099-16-8



(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 11 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
(NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

(Group Name)	(Substance Name)	CAS No.
PFOS, & (PFOS, its salts & derivatives)	(POSF) Perfluorooctane sulfonyl fluoride (POSF)	307-35-7
	(PFOS-Mg) Perfluorooctanesulfonic acid, magnesium salt (PFOS-Mg)	91036-71-4
	(PFOS-Na) Perfluorooctanesulfonic acid, sodium salt (PFOS-Na)	4021-47-0
	Piperidine 1,1,2,2,3,3,4,4,5,5,6,6,7,7,8,8,8-heptadecafluorooctanesulfonate	71463-74-6
PFOA, & (PFOA, its salts & derivatives)	(Perfluorooctanoic acid) (PFOA)	335-67-1
	(PFO A - N a) Sodium perfluorooctanoate (PFOA-Na)	335-95-5
	(PFO A - K) Potassium perfluorooctanoate (PFOA-K)	2395-00-8
	(PFOA-Ag) Silver perfluorooctanote (PFOA-Ag)	335-93-3
	(PFOA-F) Perfluorooctanoyl fluoride (PFOA-F)	335-66-0
	(APFO) Ammonium pentadecafluorooctanoate (APFO)	3825-26-1
	(PFOA-Li) Lithium perfluorooctanoate (PFOA-Li)	17125-58-5



(No.): ETR24301210

(Date): 15-Mar-2024


(Page): 12 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

/ Analytical flow chart of heavy metal

These samples were dissolved totally by pre-conditioning method according to below flow chart.

Cr⁶⁺ test method excluded





(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 13 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

/ Flow chart of stripping method for metal analysis

/ The plating layer

of samples were dissolved totally by pre-conditioning method according to below flow chart.

Cr ⁶⁺ test method excluded		
/ Preparation		
/ Sample measurement (weight)		
/ Prepare suitable acid solution		
/ Put sample into acid solution		
/ Dissolve plating layer		
/ Solution		
Γ		



(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 14 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
(NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

/ Analytical flow chart - PBBs/PBDEs

/ First testing process
/ Optional screen process
/ Confirmation process

/ Sample pretreatment

/ Screen analysis

/ Sample extraction
/ Soxhlet method

/
Concentrate/Dilute extracted solution

/ Filter

/ GC/MS

/ Data



(No.): ETR24301210


(Date): 15-Mar-2024

(Page): 15 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

/ Analytical flow chart - Phthalate

/Test method: IEC 62321-8






(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 16 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
(NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

/ Analytical flow chart - HBCDD






(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 17 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

/ Analytical flow chart - Halogen






(No.): ETR24301210 (Date): 15-Mar-2024 (Page): 18 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
(NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

(/ / /) / Analytical flow chart - PFAS (including PFOA/PFOS/its related compound, etc.)





(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 19 of 23

(EVERLIGHT ELECTRONICS CO., LTD.) (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

Analytical flow chart - PAHs (Polycyclic Aromatic Hydrocarbons) Sample pretreatment) / Sample extracted (ultrasonic extraction) by toluene solvent Analysis was performed by GC/MS / Data



(No.): ETR24301210

(Date): 15-Mar-2024


(Page): 20 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
3 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

() / Analytical flow chart of elements (Heavy metal included)

These samples were dissolved totally by pre-conditioning method according to below flow chart.

/Reference method US EPA 3051A US EPA 3052



* US EPA 3051A

/ US EPA 3051A method does not add HF.



(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 21 of 23


(EVERLIGHT ELECTRONICS CO., LTD.)
(NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

ICP-OFS

(Flow chart of digestion for the elements analysis performed by ICP-OES)

/ These samples were dissolved totally by

pre-conditioning method according to below flow chart.



, , , / Steel, copper, aluminum, solder	, , , , Aqua regia, $\rm HNO_3$, $\rm HCI$, $\rm HF$, $\rm H_2O_2$
/ Glass	, / HNO ₃ ,HF
, , , / Gold, platinum, palladium, ceramic	/ Aqua regia
/ Silver	/ HNO ₃
/ Plastic	, , , / H ₂ SO ₄ , H ₂ O ₂ , HNO ₃ , HCI
/ Others	/ Added appropriate reagent to total digestion



(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 22 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)

6-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)

* / . *

(The tested sample / part is marked by an arrow if it's shown on the photo.)



ETR24301210 NO.2





(No.): ETR24301210

(Date): 15-Mar-2024

(Page): 23 of 23

(EVERLIGHT ELECTRONICS CO., LTD.)
-8 (NO. 6-8, ZHONGHUA RD., SHULIN DIST., NEW TAIPEI CITY 23860, TAIWAN)





* (End of Report) **